

Technical Data Sheet
HIFLEX – FR 410 G/MV

Test Items		Unit	Average Value
Weight		Gsm	410±10
Yarn		DxD	500x500 (High Strength)
Thread		/Inch	9x9
Peel Strength		N	≥30
Pull Strength	Longitude	N	850
	Latitude	N	780
Elongate Rate	Longitude	%	28
	Latitude	%	27
Tear Strength	Longitude	N	210
	Latitude	N	210

Attention:

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use which are beyond our knowledge and control any guarantee and liability cannot be accepted.